



## PVC FLEX

### DESCRIPTION

Material for plotter cutting applications

### SPECIFICATION

Size: 50cm x 50m  
N.W: 10,6 kg / roll

### TRANSFER CONDITION

The following instructions are given as guideline only.  
Temperature: 160° C ( 320° F)  
Pressing Time: 10 - 12 seconds

### SUITABLE FOR

Cotton, mixtures of polyester / cotton and polyester / acrylic or for similar textile.  
Not suitable for treated and dyed garments.

### NOTICE

We offer you to test the product against the color migration. Pressing instruction may change, according to the fabric type.

### ÜRÜN TANIMI

Plotter kesin uygulamaları için malzeme

### ÖZELLİKLER

Ebat: 50cm x 50m  
Net Ağırlık: 10,6 kg / roll

### BASKI TALİMATLARI

Aşağıdaki talimatlar sadece normal şartlarda göredir.  
Derece: 160° C ( 320° F)  
Baskı Süresi: 10 - 12 saniye

### UYGUN KUMAŞLAR


Pamuk, polyester / pamuk karışımı, polyester / akrilik vb. tekstiller için uygundur.  
Boyanmış ve işlem görmüş kumaşlar için uygun değildir.

### UYARI


Boyalı kumaşlarda migrasyon ihtimaline karşı üretim öncesi gerekli testlerin yapılmasını öneririz. Kullanılacak kumaşın içeriğine göre, basım talimatları değişebilir.




Cut the image in reverse  
Deseni tersten kesiniz.




160° C ( 320° F)




4 Bar pressure  
4 Bar basınç




10-12 seconds for pressing  
10-12 saniye presleme



COOL Peel  
Soğuk çekim



45°



After 24H with application  
Uygulamadan 24 saat sonra



Oruç reis mahallesi.Giyimkent sitesi.1.sokak. B3 blok 51/A, 34000 ESENLER/İstanbul



(0212) 438 73 74 | 0532 170 12 82 | 0532 597 39 15



info@zetzan.com



zetzantekstil